

CSK-9802 End-ring Adhesives (rotary screen)

APPLICATIONS

Glue metal end-rings to nickel rotary screens.

GENERAL CHARACTERISTICS

Two-component adhesive (Part A and B)
Highly resistant to shock and vibration

DIRECTIONS FOR USE

Mix 1 part of Part A with 0.8 part of Part B by weight and the Part A must be more than Part B. Use within 120 minutes. To obtain optimal adhesion, degrease the end-rings surface. Apply an even coating of the prepared mixture to both end-rings and to the inside of the screen. Fit the end-rings into the screen. Let cure for 24 hours at room temperature, for 2 hours at 158°F (70°C), or for 15 minutes at 302°F (150°C)

HEALTH AND SAFETY

Before using, refer to appropriate material safety data sheets.

STORAGE

When sealed in the original container and stored in cool conditions, CSK chemical products will maintain their original properties for one year from the date of production.

PACKAGING

*Part A is available in 1 kilogram containers
*Part B is available in 0.8 kilogram containers

Products manufactured in China

ADDITIONAL INFORMATION

For additional product information, please contact with us.

Thank you for choosing **CSK**.

This data sheet is for your information, a legally binding guarantee of the product's suitability for a peculiar application cannot be derived. No responsibilities can be undertaken for occurring damages. Our products are subject to a continuous production and quality control and leave our factory in perfect condition.
Replaces technical information dated 2009/01/04 Update: 2010/01/05

